



SkimCoat

SUPER FINE POWDER

LIQUID

Pure-Coat Premium
SUPER FINE
SkimCoat
INTERIOR / EXTERIOR
WHITE

- ✓ Fixes wall imperfections from 0.5mm to 2mm thickness
- ✓ Smoothens surface imperfections
- ✓ Covers pinholes & surface unevenness
- ✓ Eliminates plastering defects, water seepage, bridges hairline cracks
- ✓ Long pot life and open time for a premium finish
- ✓ Provides superior adhesion
- ✓ Improves alkali resistance
- ✓ Good sanding properties

20 Kg

Pure-Coat Premium
SkimCoat
(Masonry Rendering Paste)

LEAD SAFE PAINT
www.lead-safe-paint.org

for both **INTERIOR & EXTERIOR SURFACES**





SUPER FINE SkimCoat POWDER

PureCoat Premium Super Fine SkimCoat (Powder) Interior/Exterior White is a powder type skimcoat based on a high performing polymer powder especially designed to smoothen surface imperfections of concrete walls prior to painting. It covers pinholes, minor concrete imperfections and unevenness that helps lessen paint consumption.

SkimCoat LIQUID

PureCoat Premium SkimCoat Liquid (Masonry Rendering Paste) is a "lead safe" special acrylic masonry rendering paste, designed to be mixed with cement and applied on concrete surfaces to smoothen surface imperfections prior to painting. It eliminates plastering defects, water seepage, bridges hairline cracks and provides superior adhesion, water and alkali resistance.

PRODUCT PREPARATION

Mix until a homogeneous and lump-free paste is attained. Let it stand for 10 to 15 minutes before mixing again prior to application.



20 kg

+



7 L water



1-part

+



½-1-part

Mix until a homogenous and lump-free paste is attained.

DIRECTION FOR USE

Apply mixture using a clean steel trowel to a desired thickness range of 0.50 - 2mm. Allow 1st coat to set for 30 minutes before applying 2nd coat. Do not add more water to the mixture during application to extend pot life as this will affect the properties of the product.



Apply mixture on a pre-moisten concrete surface using a clean steel trowel to a desired thickness range of 0.50 - 3mm. Allow surface to dry for 30 minutes before sanding. Allow at least 4 days curing time before painting. No need to apply concrete neutralizer.

*For optimal performance and durability, it is recommended to use PureCoat Premium SkimCoat Liquid in place of water when mixing with PureCoat Premium Super Fine SkimCoat (Powder).

COVERAGE (at 1mm dry film thickness)

20 - 25 sqm per 20kg bag



1.00 - 1.25 sqm per kg mixture

POT LIFE

3 - 4 hours



30 minutes

DRYING TIME

Recoat: 30 minutes
Curing: 24 hours
Paint Ready: 24 hours



Recoat: 30 minutes
Curing: 24 hours
Paint Ready: 24 hours

PACKAGING SIZE

20kg - bag



4 liter & 16 liter plastic pail

SURFACE PREPARATION

For maximum SkimCoat performance, surface to be applied must be dry and in sound condition, free from loose dirt, dust, oil, grease and other foreign matter.

HEALTH AND SAFETY INFORMATION - Please refer to safety data sheet for further information.



Sycwin Coating & Wires, Inc.

93 Joy St., Grace Village, Balingasa, Quezon City 1115 Philippines
Tel: (632) 83646001 to 06; 83645790; 34113491 to 93 • Fax: (632) 83643870

Email address: sales@sycwin.com • Web: www.sycwin.com

Like us at www.facebook.com/sycwinpaints